

IMPAX PC - POLYCARBONATE

IMPAX PC PROPERTIES	VALUE	UNIT	TEST METHOD
GENERAL			
Density	1.2	g/cm ³	ISO 1183-1:2019 Method A
Water Absorption	0.2	%	ISO 62:2008
MECHANICAL			
Tensile Strength	60	MPa	ISO 527-2:2012
Tensile Strain at Break	80	%	ISO 527-2:2012
Tensile Modulus	2300	MPa	ISO 527-2:2012
Flexural Strength	90	MPa	ISO 178:2019 Method A,B
Flexural Modulus	2300	MPa	ISO 178:2019 Method A,B
Charpy Impact Strength, Notched	40	kJ/m ²	ISO 179-1:2010
Izod Impact Strength, Notched	70	kJ/m ²	ISO 180:2000+Amd.2:2013
Rockwell Hardness, L-scale	100		ASTM D785
Rockwell Hardness, M-scale	N/A		ASTM D785
Rockwell Hardness, R-scale	N/A		ASTM D785
THERMAL			
Vicat Softening Temperature	135	°C	ISO 306:2013
Heat Deflection Temperature, 1.82MPa	125	°C	DIN53752
Coefficient of Linear Thermal Expansion	7	m/m.K x 10 ⁻⁵	DIN53752
Self Ignition Temperature	550	°C	ASTM D 1929
Flash Ignition Temperature	480	°C	ASTM D 1929
Glow Wire Ignition Temperature (3 mm)	900	°C	IEC 60695-2-13
Burning Behaviour, Vertical	N/A		UL 94-2013/ Rev.9-2018 Section 8
Burning Behaviour, Horizontal (1.5 mm)	HB		UL 94-2013/ Rev.9-2018 Section 7
Continuous Service Temperature	110	°C	
Short Term Service Maximum Temperature	120	°C	
Moulding Range	200-260	°C	
OPTICAL			
Light Transmission Clear (3mm)	88	%	520nm
Light Transmission Grey (3mm)	50	%	520nm
Light Transmission Opal (3mm)	20	%	520nm
Refractive Index	1.59	n _D	DIN5036-3
Haze	<0.8	%	ISO 14782

Product Disclaimer: This information provides reliable and accurate data to the best of our knowledge at the time of publishing. Due to our inability to control conditions of use and application, we are unable to make any recommendations or suggestions. The EGR Group (Oakmoore Pty Ltd) assumes no liability for use of information presented herein.